

# Acrylic Resurfacer

## 55 Gallon Drum Method

**MIXING DEVICE:** 1 or 1.5 hp 3/4" drill with 55 gallon drum paddle mixer

<b>Acrylic Resurfacer</b>	55 gallon drum
Silica Sand	800 lbs. (50-60 Mesh)
Water	Min. 22 gal./Max. 38.50 gal.

<b>Acrylic Resurfacer</b>	10 gallons
Silica Sand	120-180 lbs. (50-60 Mesh)
Water	4 - 7 gallons

1. Start with 1 Full drum of Acrylic Resurfacer and 2 clean, empty drums.
  2. Split 1 drum of Concentrate material evenly into 3 drums.
  3. You will have 18 1/3 gallons in each drum
  4. While continuously mixing material, slowly add 266 lbs. sand to each drum.
  5. After sand is thoroughly mixed into concentrate, add 12 gallons of clean water to each drum and mix until all parts are combined into a creamy consistency.
- Note:** During hot temperatures use max. range of water dilution, but do not exceed!

