



Color Concentrate With Sand

CMT - 2

Revised: 4/05

1. PRODUCT NAME:

Color Concentrate
With Sand

2. MANUFACTURER:

ThorWorks Industries, Inc.
2520 S. Campbell St.
Sandusky, OH 44870
Phone: 800-326-1994
Fax: 419-626-5477
www.thorworks.com

Additional Plant Locations:
SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone 1-800-395-7325 or visit
www.sealmaster.net to find the location near you.

3. PRODUCT DESCRIPTION & BENEFITS:

SportMaster Color Concentrate With Sand is a 100% acrylic emulsion coating designed for tennis courts and other sport and recreational pavement surfaces.

Color: Available in Sherwood Green, Forest Green, Light Green, Red, Beige, Blue, Brown, Grey, and Maroon.

Uses: Tennis courts, basketball courts, and other asphalt or concrete multi-purpose surfaces.

4. SURFACE PREPARATION:

Pavement surface must be cleaned entirely of dust, dirt, debris and all loose materials. Repair of pavement surface defects, depressions and cracks must be completed prior to application. All repairs must be flush and smooth to adjoining surfaces.

New asphalt surfaces must cure 14 to 28 days prior to application. It is recommended that any uncoated asphalt surface receive one or more coats of Acrylic Resurfacer (Technical Bulletin CMT-3) as required by surface roughness and porosity to provide a smooth, dense underlayment for application of color texture and finish coats.

New concrete surfaces must cure

28 days prior to application. Concrete surfaces should have a medium broom finish or similar roughened texture. They must never be steel trowelled. Etch surface with Muriatic or Phosphoric Acid and apply SportMaster Acrylic SportMaster Adhesion Promoter prior to color coating.

5. MIXING PROCEDURES:

The following mix design is for a 55 gallon drum of Color Concentrate with Sand:

SportMaster Color Concentrate with Sand.....55 Gallons
Water.....20-25 Gallons

The following mix design is for a 30 gallon keg of Color Concentrate with Sand:

SportMaster Color Concentrate with Sand.....30 Gallons
Water.....12-15 Gallons

Note: Mix material to a smooth, uniform consistency.

6. APPLICATION:

Apply mixed Concentrate With Sand with soft rubber squeegees.

Allow each coat to thoroughly dry before applying the next coat.

7. COVERAGE:

Yield calculations are based on undiluted gallons of SportMaster Concentrate With Sand and vary according to surface texture and porosity within the limits below:

Each coat requires .06 to .08 gallons per square yard.

8. DRYING TIME:

Concentrate With Sand dries in 30 to 60 minutes under optimum drying conditions. Allow 48 hours before allowing foot traffic or play.

9. CAUTIONS:

Do not store in direct sunlight or where temperatures exceed 100°F. Do not apply if rain is imminent or forecast. Keep from freezing. Close container when not in use.

Product Data:

Type.....Acrylic

Odor.....Ammonia

Flammability.....Non-Flammable

Flash Point.....None

Storage Life.....One Year

Colors.....Several Available

Color Concentrate With Sand
CMT - 2

SealMaster
April 2005
(Supersedes CMT-2 (5/01), CMT-2 (12/02), CMT-2 (7/04))

SPORT SURFACING

Color Concentrate With Sand

10. WARRANTY:

The statements made on this technical bulletin are believed to be true and accurate, and are intended to provide a guide for approved construction practices. Manufacturer does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. Manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall Manufacturer be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or equipment furnished or work performed. Manufacturer shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

Copyright© 2005, SealMaster
All rights reserved.

ThorWorks Industries, Inc.
P.O. Box 2277
Sandusky, OH 44870

Phone: 1-800-326-1994
FAX: 1-419-626-5477

www.sportmaster.net

