



ColorPlus Pro System

CMT - 43

Revised: 3/12

1. PRODUCT NAME:
ColorPlus Pro System

2. MANUFACTURER:
ThorWorks Industries, Inc.
2520 S. Campbell St.
Sandusky, OH 44870
Phone: 800-326-1994
Fax: 419-626-5477
www.thorworks.com

Additional Plant Locations:
SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone 1-800-395-7325 or visit
www.sealmaster.net to find the location near you.

3. PRODUCT DESCRIPTION & BENEFITS:
SportMaster ColorPlus Pro is a highly pigmented coating system designed for tennis courts and other sport and recreational pavement surfaces.

ColorPlus Pro features superior hiding, vibrance, and ultra-violet fade resistance.

Color: Forest Green, *Light Green, Dark Green, Beige, Brown, *Red, Maroon, Gray, Blue, Tournament Purple, Lt. Blue, *Dove Gray, *Ice Blue, *Sandstone, Orange, and Yellow.

LEED: SS Credit 7.1:
Heat Island Effect: Non-Roof
*Specific colors may contribute toward LEED credits.

4. SURFACE PREPARATION:
Pavement surface must be cleaned entirely of dust, dirt, and debris. Repair of pavement surface defects, depressions and cracks must be completed prior to application. All repairs must be flush and smooth to adjoining surfaces.

New asphalt surfaces must cure 14 to 30 days prior to application. It is recommended that any uncoated asphalt surface receive one or more coats of Acrylic Resurfacer (Technical Bulletin CMT - 3) as required by surface roughness and porosity to provide a smooth, dense

underlayment for application of color coatings.

New concrete surfaces must cure 28 days prior to application. Concrete surfaces should have a medium broom finish or similar roughened texture. Etch surface with muriatic or phosphoric acid and apply SportMaster Acrylic Adhesion Promoter (Technical Bulletin CMT - 21), prior to color coating.

5. MIXING PROCEDURES:
Mix in the following order for 55 gallon drum of Neutral Concentrate:

- SportMaster Neutral Concentrate.....55 gallons
- SportMaster ColorPlus.....8 gallons
- Water.....28 - 33 gallons
- Silica Sand (80 to 100 mesh AFS).....400 lbs.

Mix in the following order for 30 gallon keg of Neutral Concentrate:

- SportMaster Neutral Concentrate.....30 gallons
- SportMaster ColorPlus.....4 gallons
- Water.....15 - 18 gallons
- Silica Sand (80 to 100 mesh AFS).....200 lbs.

Note: Mix thoroughly to ensure complete dispersion of ColorPlus.

6. APPLICATION:
Apply mixed coating with a soft rubber squeegee. A minimum of two coats are recommended.

7. IMPORTANT:
Stir material thoroughly before using. Temperature must be a minimum of 50° F. and rising before application. Do not apply when rain is imminent or forecast. Keep from freezing. Close container when not in use.

8. CAUTIONS:
KEEP OUT OF REACH OF CHILDREN. Do not take internally. If swallowed, call a physician immediately. In case of contact with eyes, flush immediately with water for 15 minutes and call a physician. When not in use, keep containers tightly closed and upright to prevent leakage.

9. WARRANTY:
The statements made on this technical bulletin are believed to be true and accurate, and are intended to provide a guide for approved construction practices. Manufacturer does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. Manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall Manufacturer be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or equipment furnished or work performed. Manufacturer shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

Copyright© 2012, SealMaster
All rights reserved.

ThorWorks Industries, Inc.
P.O. Box 2277
Sandusky, OH 44870
Phone: 1-800-326-1994
FAX: 1-419-626-5477

www.sportmaster.net

Product Data:

Type.....	Water Based Pigment Dispersion
Flammability.....	Non Flammable
Flash Point.....	None
Colors.....	Several Available