



# Neutral Concentrate

CMT - 38

Revised: 8/09

## 1. PRODUCT NAME:

Neutral Concentrate

## 2. MANUFACTURER:

ThorWorks Industries, Inc.  
2520 S. Campbell St.  
Sandusky, OH 44870  
Phone: 800-326-1994  
Fax: 419-626-5477  
www.thorworks.com

### Additional Plant Locations:

SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone 1-800-395-7325 or visit  
www.sealmaster.net to find the location near you.

## 3. PRODUCT DESCRIPTION & BENEFITS:

SportMaster- Neutral Concentrate is a 100% acrylic emulsion coating formulated for tennis courts and other sport and recreational pavement surfaces. Neutral Concentrate is designed to be mixed with SportMaster ColorPlus pigment dispersion to achieve desired color.

**Uses:** Tennis courts, basketball courts, and other multipurpose pavement surfaces.

**Color:** Neutral. Desired color is achieved by mixing ColorPlus pigment dispersion with Neutral Concentrate.

**Surface Preparation:** Pavement surface must be cleaned entirely of dust, dirt, and debris. Repair of pavement surface defects, depressions and cracks must be completed prior to application. All repairs must be flush and smooth to adjoining surfaces.

**New asphalt surfaces** must cure 14 to 30 days prior to application. It is recommended that any uncoated asphalt surface receive one or more coats of Acrylic Resurfacer (Technical Bulletin CMT - 3) as required by surface roughness and porosity to provide a smooth, dense underlayment for application of color coatings.

**New concrete surfaces** must cure 28 days prior to application. Concrete surfaces should have a medium broom finish or similar roughened texture. Etch surface with muriatic or phosphoric acid and apply SportMaster Acrylic Adhesion Promoter (Technical Bulletin CMT - 21).

## 4. MIXING PROCEDURES:

Mix in the following order for 55 gallon drum of Neutral Concentrate:

SportMaster  
Neutral Concentrate.....55 gallons  
SportMaster ColorPlus.....4 gallons  
Water.....28-33 gallons  
Silica Sand (80 to 100 mesh).....400 lbs.

Mix in the following order for 30 gallon keg of Neutral Concentrate:

SportMaster  
Neutral Concentrate.....30 gallons  
SportMaster ColorPlus.....2 gallons  
Water.....15-18 gallons  
Silica Sand (80 to 100 mesh).....200 lbs.

Neutral Concentrate can also be used as a resurfacer by using the following mix design:

SportMaster  
Neutral Concentrate.....55 gallons  
Water.....28-33 gallons  
Silica Sand (50 to 60 mesh).....600 lbs.

SportMaster  
Neutral Concentrate.....30 gallons  
Water.....15-18 gallons  
Silica Sand (50 to 60 mesh).....300 lbs.

**Note:** Mix thoroughly to ensure complete dispersion of ColorPlus.

## 5. APPLICATION:

Apply mixed coating with a soft rubber squeegee. A minimum of two coats are recommended.

## 6. IMPORTANT:

Stir material thoroughly before using. Temperature must be a

minimum of 50° F. and rising before application. Do not apply when rain is imminent or forecast. Keep from freezing. Close container when not in use.

## 7. COVERAGE:

Yield calculations are based on undiluted gallons of Neutral Concentrate and vary according to surface texture and porosity within the limits below:

.05 to .07 gallon per square yard per coat

## 8. DRYING TIME:

Neutral Concentrate dries in 30 to 60 minutes under optimum drying conditions. Allow each coat of material to dry thoroughly before applying successive coats. Low ambient or low surface temperature and high humidity increase drying time. Allow coating to cure for 48 hours before opening up for play.

## 9. CAUTIONS:

**KEEP OUT OF REACH OF CHILDREN.** Do not take internally. If swallowed, call a physician immediately. In case of contact with eyes, flush immediately with water for 15 minutes and call a physician. When not in use, keep containers tightly closed and upright to prevent leakage.

## 10. WARRANTY:

The statements made on this technical bulletin are believed to be true and accurate, and are intended to provide a guide for approved construction practices. Manufacturer does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results

## Product Data:

Type.....	Acrylic Emulsion
Pounds per Gallon.....	8.8 ± .5
Odor.....	Slight Ammonia
Flammability.....	Non-Flammable
Flash Point.....	None

Neutral Concentrate  
CMT-38

SealMaster  
August 2009  
(Supersedes CMT-38 (7/04), CMT-38 (4/05))

SPORT SURFACING

# **Neutral Concentrate**

are all beyond our control. Manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall Manufacturer be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material or equipment furnished or work performed. Manufacturer shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

Copyright© 2009, SealMaster  
All rights reserved.

ThorWorks Industries, Inc.  
P.O. Box 2277  
Sandusky, OH 44870

Phone: 1-800-326-1994  
FAX: 1-419-626-5477

**[www.sportmaster.net](http://www.sportmaster.net)**

