



Neutral Concentrate With Sand

CMT - 40

Revised: 7/09

1. PRODUCT NAME:

Neutral Concentrate
With Sand

2. MANUFACTURER:

ThorWorks Industries, Inc.
2520 S. Campbell St.
Sandusky, OH 44870
Phone: 800-326-1994
Fax: 419-626-5477
www.thorworks.com

Additional Plant Locations:

SealMaster has a nationwide network of manufacturing and distribution facilities.

Phone 1-800-395-7325 or visit
www.sealmaster.net to find the
location near you.

3. PRODUCT DESCRIPTION & BENEFITS:

SportMaster Neutral Concentrate with Sand is a 100% acrylic emulsion coating formulated for tennis courts and other sport and recreational pavement surfaces. Neutral Concentrate with Sand is designed to be mixed with SportMaster ColorPlus pigment dispersion to achieve desired color.

Uses: Tennis courts, basketball courts, and other multipurpose pavement surfaces.

Color: Neutral. Desired color is achieved by mixing ColorPlus pigment dispersion with Neutral Concentrate with Sand.

Surface Preparation: Pavement surface must be cleaned entirely of dust, dirt, and debris. Repair of pavement surface defects, depressions and cracks must be completed prior to application. All repairs must be flush and smooth to adjoining surfaces.

New asphalt surfaces must cure 14 to 30 days prior to application. It is recommended that any uncoated asphalt surface receive one or more coats of Acrylic Resurfacer (Technical Bulletin CMT - 3) as required by surface roughness and porosity to provide a smooth, dense underlayment for application of color coatings.

New concrete surfaces must cure 28 days prior to application. Concrete surfaces should have a medium broom finish or similar roughened texture. Etch surface with muriatic or phosphoric acid and apply SportMaster Acrylic Adhesion Promoter (Technical Bulletin CMT - 21).

4. MIXING PROCEDURES:

• Mix in the following order for 55 gallon drum of Neutral Concentrate with Sand:

SportMaster
Neutral Concentrate
with Sand.....55 gallons
SportMaster ColorPlus.....4 gallons
Water.....20-25 gallons

• Mix in the following order for 30 gallon keg of Neutral Concentrate with Sand:

SportMaster
Neutral Concentrate
with Sand.....30 gallons
SportMaster ColorPlus.....2 gallons
Water.....12-15 gallons

Note: Mix thoroughly to ensure complete dispersion of ColorPlus.

5. APPLICATION:

Apply mixed coating with a soft rubber squeegee. A minimum of two coats are recommended.

6. IMPORTANT:

Stir material thoroughly before using. Temperature must be a minimum of 50° F. and rising before application. Do not apply when rain is imminent or forecast. Keep from freezing. Close container when not in use.

7. COVERAGE:

Yield calculations are based on undiluted gallons of Neutral Concentrate with Sand and vary according to surface texture and

porosity within the limits below:

.06 to .08 gallon per square yard per coat

8. DRYING TIME:

Neutral Concentrate with Sand dries in 30 to 60 minutes under optimum drying conditions. Allow each coat of material to dry thoroughly before applying successive coats. Low ambient or low surface temperature and high humidity increase drying time. Allow coating to cure for 48 hours before opening up for play.

9. CAUTIONS:

KEEP OUT OF REACH OF CHILDREN. Do not take internally. If swallowed, call a physician immediately. In case of contact with eyes, flush immediately with water for 15 minutes and call a physician. When not in use, keep containers tightly closed and upright to prevent leakage.

10. WARRANTY:

The statements made on this technical bulletin are believed to be true and accurate, and are intended to provide a guide for approved construction practices. Manufacturer does not make, nor does it authorize any agent or representative to make any warranty, express or implied, concerning this material as workmanship, weather, construction, equipment utilized and other variables affecting results are all beyond our control. Manufacturer warrants only that the material conforms to product specifications and any liability to the buyer or user of this product is limited to the replacement value of the product only. In no event shall Manufacturer be liable for any injury, loss or damage, either direct or incidental, special or consequential, however arising, in connection with material

Product Data:

Type.....	Acrylic Emulsion
Pounds per Gallon.....	8.8 ± .5
Odor.....	Slight Ammonia
Flammability.....	Non-Flammable
Flash Point.....	None

Neutral Concentrate With Sand

or equipment furnished or work performed. Manufacturer shall not, in any manner, be liable for any defects, variations or change in condition in the substructure over which its products are installed.

Copyright© 2009, SealMaster
All rights reserved.

ThorWorks Industries, Inc.
P.O. Box 2277
Sandusky, OH 44870

Phone: 1-800-326-1994
FAX: 1-419-626-5477

www.sportmaster.net

