

Specifications for applying  
**PICKLEMASTER SURFACING SYSTEM**  
over Concrete Pickleball Court Surfaces

**CMT-72**

REVISED 03/25

**PRODUCT NAME**

PickleMaster Surfacing System over concrete Pickleball court surfaces.

**DISTRIBUTION LOCATIONS**

SportMaster products are distributed through a world-wide network of stores and distributors. Call (800)395-7325 or visit [www.sportmaster.net](http://www.sportmaster.net) to find a location near you.

**1. SCOPE:**

**1.1**

The following specifications pertain to the application of the PickleMaster Surfacing System over concrete sport surfaces. Refer to Product Technical Data sheets for specific mixing and application instructions.

**1.2**

SportMaster color coating systems are designed for use on properly built sport surfaces. Refer to the American Sports Builders Association for recommended guidelines on construction of pickleball court surfaces.

**1.3**

The concrete surface must be constructed with a suitable vapor barrier beneath the slab and adequate perimeter drainage to prevent moisture accumulation beneath the surface. Do not use curing compounds on the concrete surface. Moisture curing only.

**2. SURFACE PREPARATION:**

**2.1**

New concrete surfaces must cure 28 days. Concrete surfaces should have a medium broom finish or similar roughened texture. They must never be steel troweled. If using a shot blaster to achieve texture, a shot blast profile of CSP 3 or 4 is recommended.

**2.2**

Thoroughly remove all dust, dirt, debris and loose materials.

**2.3**

Etch concrete surface with phosphoric or muriatic acid solution. Rinse clean with water after etching is complete.



**2.4**

Fill all cracks with SportMaster CrackMagic, Acrylic Crack Patch, Acrylic Patch Binder or other suitable crack fillers.

**2.5**

Repair spalled areas and level depressions or “bird baths” (1/8 inch or deeper) with SportMaster Acrylic Patch Binder or Acrylic Resurfacer patching mix.

**2.6**

Apply SportMaster Acrylic Adhesion Promoter or suitable primer over new or uncoated surfaces.

**2.7**

Apply one (1) or more coats of Acrylic Resurfacer to provide a smooth underlayment for application of the SportMaster Color System.

**3. APPLICATION OF PICKLEMASTER COLOR SYSTEM:**

**3.1**

Over properly prepared concrete surface, apply a minimum of two coats of the PickleMaster Surfacing System in accordance with manufacturer’s mixing and application instructions.

**4. LINE MARKINGS:**

**4.1**

Line markings shall be laid out according to USAPA (USA Pickleball Association) specifications.

**4.2**

After masking tape has been laid, apply SportMaster Stripe Rite line primer to seal voids between masking tape and court surface to prevent “bleed under” when SportMaster Line Paint is applied.

**4.3**

Apply a minimum of one coat of SportMaster Line Paint.

Specifications for applying  
**PICKLEMASTER SURFACING SYSTEM**  
over Concrete Pickleball Court Surfaces

**CMT-72**  
REVISED 03/25

**5. GENERAL:**

**5.1**

All work shall be performed in a workman like manner.  
All containers and debris shall be removed from job  
when completed.

Copyright© 2025, SportMaster  
All rights reserved.

ThorWorks Industries, Inc.  
P.O. Box 2277  
Sandusky, OH 44870

Phone: 1-800-326-1994  
FAX: 1-419-626-5477  
[www.sportmaster.net](http://www.sportmaster.net)