

# Flexible Acrylic Resurfacer

## 30 Gallon Keg Method

**MIXING DEVICE:** 1 or 1.5 hp 3/4" drill with 55 gallon drum paddle mixer

**Flexible Acrylic Resurfacer** 30 gallon keg  
Silica Sand 275 - 325 lbs. (50-60 Mesh)  
Water Min. 36 gal./Max. 39 gal.

**Flexible Acrylic Resurfacer** 10 gallon  
Silica Sand 100 (50-60 Mesh)  
Water 6.5 - 7 gallons

1. Start with 1 full keg of Flexible Acrylic Resurfacer and 2 clean, empty kegs.
  2. Split 1 keg of Concentrate material evenly into 3 kegs.
  3. You will have 10 gallons in each keg.
  4. Pour 7 gallons of clean water into each keg and mix well.
  5. While continuously mixing material, slowly add 100 lbs. of sand to each keg and mix until all parts are combined into a creamy consistency.
- Note:** During hot temperatures use max. range of water dilution, but do not exceed!

