

Flexible Acrylic Resurfacer

55 Gallon Drum Method

MIXING DEVICE: 1 or 1.5 hp 3/4" drill with 55 gallon drum paddle mixer

Flexible Acrylic Resurfacer 55 gallon drum
Silica Sand 500 to 600 lbs. (50-60 Mesh)
Water Min. 36 gal./Max. 39 gal.

Flexible Acrylic Resurfacer 10 gallons
Silica Sand 100 lbs. (50-60 Mesh)
Water 6.5 - 7 gallons

1. Start with 1 full drum of Flexible Acrylic Resurfacer and 2 clean, empty drums.
2. Split 1 drum of Concentrate material evenly into 3 drums.
3. You will have 18 1/3 gallons in each drum.
4. Pour 13 gallons of water into each drum and mix well.
5. While continuously mixing material, slowly add 185 lbs sand to each drum and mix until all parts are combined into a creamy consistency.

Note: During hot temperatures use max. range of water dilution, but do not exceed!

